



45 KT

TEKNISK DATA

Tvättad sand
 Kornform: kantrund
 Medelkornstorlek: 0,457 mm ± 0,020
 Kornkoncentration: 72,3
 Teo.specifika ytan: 58 cm²/g
 Sintringstemp: >1200°C
 Glödningsförlust vid 900°C: 0,17 %



Masköppning mm	ASTM nr.	Sand på sikt (%)	Sand genom sikt (%)	Kemisk analys (%)
1,41	14	0	0	SiO ₂ 94,5
1,00	18	0	100	Al ₂ O ₃ 3,0
0,71	25	2,0	98,0	Fe ₂ O ₃ 0,28
0,50	35	19,0	79,0	CaO 0,21
0,355	45	47,1	31,9	MgO 0,04
0,25	60	27,0	4,9	Na ₂ O 0,48
0,18	80	4,3	0,6	K ₂ O 1,3
0,125	120	0,6	0	
0,09	170	0	0	
0,063	230	0	0	
panna	0	0	0	

